

**MONOLITHIC ROOF BIT CUTTING BIT INSERT**RELATED APPLICATIONS

This application is related to copending U.S. patent application No. 09/591,644, filed June 9, 2000, to Curnie A. Dunn et al. (Case No. K-1554P), entitled "DRILL BIT, HARD MEMBER AND BIT BODY" and patent application No. 09/500,813, filed February 15, 2000, by Dunn et al.

FIELD OF THE INVENTION

The invention pertains to an earth penetrating rotary drill bit that has a hard member at the axial forward end of a bit body.

BACKGROUND OF THE INVENTION

The expansion of an underground coal mine requires digging a tunnel that initially has an unsupported roof. To provide support for the roof, a rotary drill bit (e.g., a roof drill bit) is used to drill boreholes, which can extend from between about two feet to about (or even greater than) twenty feet, into the earth strata. Roof bolts are affixed within the boreholes and a roof support (e.g., a roof panel) is then attached to the roof bolts. Examples of a conventional roof drill bit with an axial forward slot that carries a blade style hard insert are shown in U.S. Patent No. 5,172,775 to Sheirer et al.

It is desirable to provide a roof drill bit that permits completion of the drilling operation as soon as possible. A roof drill bit that presents at least three leading cutting edges increases the penetration rate due to an increase in the number of the leading cutting edges. Three leading cutting edges, especially with a radial orientation, permits the roof drill bit to advance forward with very little

the roof drill bit to advance forward with very little wobble (i.e., side-to-side movement) so as to achieve balanced drilling. Leading cutting edges that terminate short (i.e., at a point radially outward) of the center point of the hard insert define a central open area so as to reduce the amount of low velocity cutting, i.e., the cutting action that occurs nearer to the center point. An increase in the number of the leading cutting edges, the balanced drilling, and the reduction in low velocity drilling each contributes to an increase in the penetration rate of the roof drill bit, which provides for the efficient completion of the drilling operation.

Clogging and stalling may occur when drilling at a higher penetration rate. It would be an advantage to adequately handle and evacuate debris so as to reduce the potential for clogging. A roof bit drill that pulverize earth strata at the tip of the bit into manageable small sized particles that can be easily evacuated. It would be an advantage to provide a roof drill bit with a drill bit body that can withstand the stresses inherent during stalling.

#### SUMMARY OF THE INVENTION

In one form thereof, the invention is a rotary drill bit for penetrating the earth strata. The drill bit includes a bit body that has an axial forward end wherein a hard insert, which preferably is monolithic, is affixed to the axial forward end thereof. The hard insert presents at least three leading cutting edges.

In yet another form thereof, the invention is a hard member, which preferably is monolithic, that attaches to a drill bit body with a central longitudinal axis so as to form a rotary drill bit. The hard member has a forward surface and a rearward

surface. At least three discrete leading cutting edges project from the forward surface of the hard member. Each cutting edge is not straight but has an irregular nonlinear shape. In one embodiment the leading cutting  
5 edge is stepped. It is believed that the stepped cutting edge provides for disintegration of earth strata into smaller sized particles than a straight cutting edge.

In a form of the invention is a roof drill  
10 bit body for attachment to a hard member so as to form a rotary drill bit for penetrating earth strata that generates debris wherein the drill bit body comprises a central bore, and a peripheral surface. The peripheral surface contains a trio of debris apertures wherein  
15 each aperture is in communication with the central bore.

#### BRIEF DESCRIPTION OF THE DRAWINGS

The following is a brief description of the drawings that form a part of this patent application.

20 FIG. 1 is an perspective view of a specific embodiment of a roof drill;

FIG. 2 is an isometric view of the hard insert of FIG. 1;

25 FIG. 3 is a perspective view of the hard insert of FIG. 1 in a second position;

FIG. 4 is a partial cross section of a view of the hard insert taken along lines 4--4 in FIG. 3; and

30 FIG. 5 is a side view of roof drill bit hard insert shown in FIGS. 1-3 ;

#### DETAILED DESCRIPTION OF THE INVENTION

Referring to the drawings, there is a roof drill bit generally designated as 20 with a central longitudinal axis A-A. Roof drill bit 20 includes a

2025 RELEASE UNDER E.O. 14176

generally cylindrical elongate steel drill bit body 22 having a diameter equal to 1 inch (2.54 cm). Bit body 22 further includes an axial forward end 24, an axial rearward end 26, the axial rearward end has a generally cylindrical peripheral surface.

There is a pedestal portion at the axial forward end 24. Pedestal portion includes a trio of symmetric arcuate dished-out scalloped surfaces that become narrower (not shown), as well as shallower, as they move in an axial rearward direction. Debris ports 38 permit evacuation of the drilling debris, including larger size pieces of debris, under the influence of a vacuum in dry drilling. The roof drill bit is also useful for wet drilling.

15           There is a braze joint between the surface of  
the drill bit body at the axial forward end thereof and  
the rearward surface of the hard insert. The pedestal  
portion near its axial forward end either includes a  
trio of dished out pedestal lobes or a pedestal  
20 projection having a trio of symmetric lobes for  
cooperating respectively with corresponding three prong  
lobe projections 62 or, alternatively, three dished out  
lobes for forming a connection between the insert 56  
and bit body 22. U.S. patent application serial number  
25 09/591,664, filed June 9, 2000, to Curnie A. Dunn  
et al. (Case No. K-1554P) is herein incorporated by  
reference in its entirety.

The roof drill bit hard insert 56 further presents three discrete leading cutting edges 76.

30 However, there may be more than three discrete leading cutting edges depending upon the application.

The hard insert 56 is preferably (but not necessarily) a single monolithic member formed by powder metallurgical techniques from a hard material such as a cemented (e.g., cobalt) tungsten carbide alloy wherein a powder mixture is pressed into a green



approximately thirty (30) degrees along its entire length. The lower step portion has a generally planar relief top surface 90 oriented at a constant relief angle of approximately twenty-one (21) degrees. The transition portion has a generally planar top surface 88 oriented at a constant relief angle of approximately eighteen 18 degrees. The upper relief angle can range between 15-40 degrees, the transition relief angle between 5-30 degrees and the lower relief angle between 5-30 degrees as may be determined adequate by an ordinary artisan. The proper relief angles required to maintain speed and performance are well-known to be related to the cutting operation and earth strata being penetrated. The cutting edge 76 has a chamfer 92 as are commonly used in the art along the top surface thereof to reduce chipping of the cutting edge.

Each lobe 64 further includes a distal peripheral surface 74. The lower leading surface 66 intersects the distal peripheral surface 74 to form a generally straight side clearance cutting edge 78 at the intersection thereof. The rake surfaces 66 and 65 intersect the top surface of a lobe so as to form a stepped leading cutting edge 76 at the intersection thereof. An upper step of the leading cutting edge is connected to a lower step by a transition section. The upper step and lower step are formed along parallel lines, the leading cutting edges are both disposed at the same downward angle  $Z$  with respect to the horizontal as shown in figure 4. Angle  $Z$  makes an angle between 5-35 degrees with respect to the horizontal. The angle  $Z$  illustrated in figure 4 is 20 degrees. A transition cutting edge forms the transition between the upper step and lowers step cutting edge. The transition cutting edge is inclined at an angle of between 35-75 degrees. In figure 4 the

00000404.062501

transition edge is oriented at 55 degrees with respect to the horizontal.

A central section of the transition portion has a cutting edge 76 that is generally straight at  
5 said central section and has two rounded portions at both ends of the central straight edge section. As best seen in figure 4 a rounded concave cutting edge section 83 forms a smooth transition between the lower  
10 step 84 and the transition section 82 and a rounded convex cutting edge section 81 forms a smooth transition between the transition section 82 and upper  
step portion 80. The rounded concave section 83 and rounded convex section 81 have a radius of curvature of between .03 and .12 inches, a radius of .06 inches for  
15 both the concave 83 and convex 81 sections works effectively for a cutting edge used in earth material of general hardness and composition.

It is believed that the stepped cutting edge improves the disintegration of materials into smaller  
20 cuttings in comparison to a straight line leading cutting edge as disclosed in U.S. patent application serial number 09/591,644. The smaller cuttings result in less plugging of the central vacuum line. When a bit body identical to the instant application is  
25 substituted for a prior art monolithic 3-blade insert, such as disclosed in 09/591,644, the roof bit drill employing an insert according to the instant application can be run at full throttle whereas with the roof bit in 09/591,644 it might occasionally be  
30 required to back off the throttle (also known as "feathered").

Referring back to the geometry of the upper step leading cutting edge and lower step leading cutting edge and side cutting edge, while the upper and  
35 lower sections cutting edges and side cutting edge are generally straight and the leading cutting edge relief

2025 RELEASE UNDER E.O. 14176

top surfaces planar and perform in an acceptable fashion, other cutting edge geometries are acceptable for use. For example, the following patent documents disclose suitable cutting edge geometries: U.S. Patent  
5 No. 4,787,464 to Ojanen, U.S. Patent No. 5,172,775 to Sheirer et al., U.S. Patent No. 5,184,689 to Sheirer et al., U.S. Patent No. 5,429,199 to Sheirer et al., and U.S. Patent No. 5,467,837 to Miller et al. Each one of the above patents is hereby incorporated by  
10 reference herein.

Referring to FIG. 2, the leading cutting edges 76 of the hard insert 56 have a generally radial orientation. A line laying along each leading cutting edge when extended in a radial inward direction passes  
15 through central longitudinal axis A-A of the roof drill bit 20.

Each one of the leading cutting edges 76 begins at a point that is a distance radially outward from the central axis of the hard insert 56. The  
20 distance K is typically between 1/16-3/16 inches and in a preferred embodiment for earth strata of typical hardness is 1/8 inches from the central axis. Each leading cutting edge 76 has an upper step that extends in a radial outward direction to a transition portion.  
25 The upper step has a cutting edge length of between 1/8-1/4 inch. The upper step cutting edge preferably being approximately 1/8 inches in length so as to generate acceptable size cuttings when drilling typical earth strata. For other types of earth strata being  
30 drilled the upper step cutting edge accordingly might have a length of about 1/4 inch so as to disintegrate the material into adequately small sizes to enter into dust openings 38.

The transition portion rises a vertical  
35 height of generally between 1/16-1/8 inches from the lower step to the upper step. For earth strata of

2025 RELEASE UNDER E.O. 14176







hardness greater than both the bit body and the material that the remainder of the drill bit insert 56 is constructed from. The small cutting elements are received in sockets formed in a bit insert body and 5 brazed therein. Such sockets and integration of separate substrates into an integral body are well-known in industry. To construct a socket and a two stepped cutting element for each lobe of applicants' invention would fall within the realm of the 10 capabilities of an ordinary artisan.

The patents and other documents identified herein are hereby incorporated by reference herein.

Other embodiments of the invention will be apparent to those skilled in the art from a consideration of the specification (including the drawings) or practice of the invention disclosed herein. It is intended that the specification and examples be considered as illustrative only, with the true scope and spirit of the invention being indicated by the following claims.